

| | Value | Test Method |
|----------------------------------|-------|---|
| Coatings: | - | |
| Heat resistance [°C] | 600 | acc. to ISO 787-21 |
| Light fastness [full shade] | 8 | acc. to DIN EN ISO 16474-2/DIN EN ISO 105-B02 |
| Light fastness [1/9 SD] | 8 | acc. to DIN EN ISO 16474-2/DIN EN ISO 105-B02 |
| Weather fastness [full shade] | 5 | acc. to DIN EN ISO 16474-2/DIN EN ISO 20105-A02 |
| Weather fastness [1/9 SD] | 5 | acc. to DIN EN ISO 16474-2/DIN EN ISO 20105-A02 |
| Plastics: | - | |
| Heat resistance [full shade][°C] | >320 | acc. to DIN EN 12877-2 |
| Heat resistance [1:3][°C] | >320 | acc. to DIN EN 12877-2 |
| Light fastness [full shade] | 8 | acc. to DIN EN ISO 4892-2/DIN EN ISO 105-B02 |
| Light fastness [1:3] | 8 | acc. to DIN EN ISO 4892-2/DIN EN ISO 105-B02 |

Heat resistance: For coatings tested in heat resistant coating up to 600 °C for 30 minutes, for plastics tested in HDPE system up to 320 °C.

Light Fastness: For coatings tested in water based automotive system, for plastics tested in LDPE system. Rating with 8-step wool scale: 1=poor, 8=excellent.

Weather fastness: Tested in water based automotive system. Rating with gray scale after 2000 h accelerated weathering: 1=poor, 5=excellent.

Packaging and Handling

| | |
|-----------|---|
| Packaging | 20 kg paper bags |
| Packaging | Different types of packaging are available on request |

Tds-hd_550-01_02

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.