

Heubach formulation No. 552-06

02/10

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Component A</b>			
Modified polyamine adduct	Aradur 3986, 40%	Huntsman	30.84
Defoamer	Byk 012	Byk-Chemie	0.35
	Demi. water		14.31
Rheology modifier	Optigel WX	Rockwood	0.35
Antisettling agent	Aerosil R 972	Evonik	0.70
<b>Mix.</b>			
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	6.45
Magnesium silicate	Luzenac 10 MO	Luzenac	8.78
Mica/Quartz/Chlorite	Plastorit 0000	Imerys Talc	9.05
Titanium dioxide	Kronos 2190	Kronos	5.02
<b>Add. Disperse 45 min 4000 rpm. Temperature &lt; 40 °C.</b>			
	Demi. water		2.31
Wetting agent	Byk-346	Byk-Chemie	0.14
Levelling agent	Byk-380N	Byk-Chemie	0.70
			<b>79.00</b>
<b>Component B</b>			
Epoxy	Araldite PZ 756/67W	Huntsman	21.00
			<b>21.00</b>
			<b>100.00</b>
<b>Mix components A and B thoroughly prior to use.</b>			
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			21.4
PVC in %			29.9
PVC / CPVC			0.6

# HEUCOPHOS<sup>®</sup> ZPA

in epoxy dispersion



*Water based*

Heubach formulation No. 552-06

02/10

## SPECIFICATIONS

Solids in %

55.7

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.