

Heubach formulation No. 968-10

11/20

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Acrylic Polyol	SETALUX D A 160 X	Allnex	36.20
Solvent	Butyl acetate		5.72
Solvent	Methoxypropyl acetate		5.72
Wetting and Dispersing agent	ANTI-TERRA-204	BYK-Chemie	0.55
Thickener	Efka RM 1900, 10% in Xylene	BASF	6.65
Premix.			
Antisettling agent	AEROSIL R 972	Evonik	0.35
Magnesium silicate	Finntalc M15	MONDO MINERALS	10.90
Calcium carbonate	Omyacarb 2-AL	Omya	10.55
Titanium dioxide	KRONOS 2190	KRONOS	8.25
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	7.80
Carbon black	Lamp black 101	Orion Engineered Carbons	0.01
Grind with a bead mill.			92.70
Component B			
Curing agent	Desmodur ultra N 3390 BA	Covestro	7.30
			7.30
Mix components A and B thoroughly prior to use.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			22.0
PVC in %			32.8
PVC / CPVC			0.6
Solids in %			66.8

HEUCOPHOS[®] ZPA

In 2-part polyurethane



Solvent based

Heubach formulation No. 968-10

11/20

SPECIFICATIONS

Crosslinking in %

100.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.