

Heubach formulation No. 01209

11/01

FUNCTION	PRODUCT	PRODUCER	PBW
Styrene-acrylic dispersion	Pliotec Ls1, 41%	Goodyear	16.00
Wetting agent	Disperbyk	Byk-Chemie	0.30
Wetting agent	Surfynol 104 E	Air Products	0.30
Defoamer	Byk-023	Byk-Chemie	0.20
Neutralizing agent	Dimethylethanolamine		0.25
Premix.			
Titanium dioxide	Kronos 2056	Kronos	10.65
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	5.00
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.55
Grind.			
Styrene-acrylic dispersion	Pliotec Ls1, 41%	Goodyear	51.70
Neutralizing agent	Dimethylethanolamine		0.25
	Water		1.00
Plasticizer	TXIB Plasticizer	Eastman	4.00
Glycol ether	Dowanol DPM	Dow	4.00
Glycol ether	Butyl diglycol ether		2.20
Ester alcohol	Texanol	Eastman	1.80
Defoamer	Byk-023	Byk-Chemie	0.20
PU-thickener	Tafigel PUR 45	Münzing	1.00
PU-thickener	Collacral PU 85	BASF	0.50
Levelling agent	Byk-301	Byk-Chemie	0.10
Add while mixing.			
			100.00

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.