

DSM NeoResins formulation No. HD-130

02/06

FUNCTION	PRODUCT	PRODUCER	PBW
	Water		7.20
Neutralizing agent	AMP-90	Angus Chemie	0.10
<b>Premix.</b>			
Dispersing agent	Disperse-Ayd W 33	Elementis	1.20
Glycol ether	Butyl glycol		4.50
Titanium dioxide	Kronos 2190	Kronos	11.20
Magnesium silicate	Micro-Talc I.T. Extra	Mondo Minerals	8.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	10.60
Carbon black paste	Hostatint-Schwarz GR 30	Clariant	1.20
<b>Grind to a fineness of &lt; 20 microns, temperature &lt; 40 °C</b>			
Styrene-acrylic dispersion	Neocryl XK-87, 50%	DSM NeoResins	53.30
Ester alcohol	Texanol	Eastman	1.70
Flash-rust inhibitor	Ser-AD FA 179	Elementis	0.30
Defoamer	Drew 210-693	Ashland	0.30
Thickener	Viscoatex 46	Coatex	0.40
<b>Add to the grind.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
PVC in %			26.6
Vol.-% Anticorrosive pigment reg. pigment/filler			34.9
Solids in %			57.7

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.