

Heubach formulation No. 192-02

02/96

FUNCTION	PRODUCT	PRODUCER	PBW
Alkyd emulsion	Resydrol AZ 436 w/45 WA	Hoechst, today Cytec	54.80
Neutralizing agent	Ammonia, 10%		1.00
Drier	Additol VXW 4940, 50% in H ₂ O	Hoechst, today Cytec	1.30
Antiskinning agent	Additol XL 297	Hoechst, today Cytec	0.30
Wetting agent	Surfynol SE-F	Air Products	0.30
Defoamer	Additol VXW 4973	Hoechst, today Cytec	0.30
	Water		12.95
PU-thickener	Rheolate 225, 25% in H ₂ O	Elementis	2.00
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	5.95
Magnesium silicate	Micro-Talc A.T. Extra	Mondo Minerals	9.85
Iron oxide red	Bayferrox 222 FM	Bayer	4.50
Calcium carbonate	Millicarb	Omya	6.75
Grind with a bead mill. Adjust pH 9.0 - 9.5 with ammonia, 10%.			
			100.00
SPECIFICATIONS			
PVC in %			26.2
PVC / CPVC			0.5
Solids in %			53.8
Vol.-% Anticorrosive pigment reg. pigment/filler			22.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.