

HEUCOSIL CTF

In silicone resin



Water based

Evonik Tego formulation No. P40W 9 002

10/20

FUNCTION	PRODUCT	PRODUCER	PBW
	Demi. water		20.30
Wetting and Dispersing agent	Tego Dispers 750 W	Evonik	1.50
Defoamer	Mineral oil defoamer		0.20
Copper chromite black spinel	HEUCODUR®-Black 9-100	Heubach	8.00
Anticorrosive pigment	HEUCOSIL CTF	Heubach	5.00
Muscovite mica	Mica TM	Aspanger	14.00
Grind with a bead mill.			
Silicone resin	Silikophen P 40/W	Evonik	45.00
	Demi. water		6.00
Add while stirring.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			26.0
PVC in %			32.2
Solids in %			50.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.