

Hexion formulation NewGen primer - SF1732

08/08

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Epoxy dispersion	EPI-REZ Resin 6520-WH-53	Hexion	30.00
Glycol ether	Dowanol PPH	Dow	2.75
Defoamer	Efka-2526	Ciba	0.25
Titanium dioxide	Ti-Pure R-960	DuPont	8.95
Calcium metasilicate	Tremin 283-600 EST	Quarzwerte	8.75
Barium sulphate	Albawhite 80	Sachtleben	6.00
Anticorrosive pigment	HEUCOPHOS® CAPP	Heubach	8.35
Mica	Mica S	Aspanger	0.65
Grind with a bead mill.			
Epoxy dispersion	EPI-REZ Resin 6520-WH-53	Hexion	14.70
Adhesion promoter	Silquest A-1871	GE Silicones	0.75
	Water		7.75
Add.			88.90
Component B			
Curing agent	EPI-CURE DPC 6870-W-53	Hexion	11.00
Flash-rust inhibitor	Corrosion inhibitor L 1	Erbslöh	0.10
Add.			11.10
Mix components A and B thoroughly prior to use.			100.00
SPECIFICATIONS			
PVC in %			28.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.