

Calcium Phosphate CP

In epoxy ester



Water based

Heubach formulation No. 06292

07/06

FUNCTION	PRODUCT	PRODUCER	PBW
Epoxy ester	Resydrol AX 237 w/70 BG	Cytec	32.30
Neutralizing agent	Ammonia, 25%		1.30
Neutralizing agent	AMP-90	Angus Chemie	0.40
	Water		37.30
Drier	Additol VXW 4940, 50% in water	Cytec	1.50
Antiskinning agent	Additol XL 297	Cytec	0.50
Iron oxide red	Bayferrox 130 FS	Bayer	6.15
Anticorrosive pigment	Calcium Phosphate CP	Heubach	5.35
Magnesium silicate	Micro-Talc A.T. Extra	Mondo Minerals	7.10
Calcium carbonate	Omyacarb 1T-AV	Omya	4.30
Antisettling agent	Winnofil SP	Solvay	0.60
Wetting agent	Additol XL 270	Cytec	0.40
Defoamer	Additol VXW 4909	Cytec	0.40
Defoamer	Additol XW 372	Cytec	0.40
Mix components in order, grind with bead mill.			
PU-thickener	Rheolate 255, 4% in H ₂ O	Elementis	0.70
	Water		1.30
Add while mixing.			
			100.00
SPECIFICATIONS			
Solids in %			46.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.