



Product Description	
Chemical characterization	Quinacridone
Color Index	Pigment Red 122
Appearance	Red powder
C.I. No.	73915
CAS No.	980-26-7

Product Description			
	Unit	Value	Test Method
Hue angle [1/3 SD]		341.1	acc. to DIN EN ISO/CIE 11664-4
1/3 SD reduction ratio		1:4.5	acc. to DIN 53235-2

Technical Data			
	Unit	Value	Test Method
Density	[g/cm ³]	typ. 1.4	acc. to ISO 787-10
Bulk volume	[l/kg]	typ. 3.8	
Specific surface	[m ² /g]	typ. 66.0	acc. to DIN ISO 66132
Oil absorption	[g/100g]	typ. 54	acc. to ISO 787-5

Fastness Properties		
Resistance to Chemicals		
	Value	Test Method
Acid	5	rating acc. to DIN EN ISO 105-A03
Alkali	5	rating acc. to DIN EN ISO 105-A03
Water	5	rating acc. to DIN EN ISO 105-A03
Butanol	3 - 4	rating acc. to DIN EN ISO 105-A03
Butylacetate	4	rating acc. to DIN EN ISO 105-A03
Xylene	4 - 5	rating acc. to DIN EN ISO 105-A03
MEK	4 - 5	rating acc. to DIN EN ISO 105-A03
White spirits	4	rating acc. to DIN EN ISO 105-A03

Acid/alkali resistance: Pigment was dipped into hydrochloric acid (10%) or soda solution (10%). Rating with gray scale: 1=poor, 5=excellent.

Solvent resistance: Pigment was dipped into solvent. Rating with gray scale: 1=poor, 5=excellent.

Tds-ml_r312202-01_02

	Value	Test Method
Overpainting fastness	5	rating acc. to DIN EN ISO 105-A03
Heat resistance [°C]	180	acc. to ISO 787-21
Light fastness [full shade]	7 - 8	acc. to DIN EN ISO 16474-2/DIN EN ISO 105-B02
Light fastness [1/3 SD]	8	acc. to DIN EN ISO 16474-2/DIN EN ISO 105-B02

Overpainting: Tested in alkyd/melamine system with 30 minutes baking time at 160 °C. Rating with gray scale: 1=poor, 5=excellent.

Heat resistance: Tested in alkyd/melamine system.

Light Fastness: Tested in water based automotive system. Rating with 8-step wool scale: 1=poor, 8=excellent.

Weather Fastness		
	Full Shade	1/3 SD
1600 h	5	4 - 5
3200 h	4 - 5	3 - 4
4800 h	4 - 5	3 - 4

Tested acc. to DIN EN ISO 16474-2 in water based automotive system. Rating with gray scale in acc. to DIN EN ISO 20105-A02: 1=poor, 5=excellent.

Application Profile	
Automotive coatings	+++
Industrial coatings	+++
Decorative coatings	+++
Coil coatings	+++
Powder coatings	

+++ Excellent choice ++ Good choice + Possible choice

Packaging and Handling	
Packaging	20 kg cardboard boxes
Packaging	Different types of packaging are available on request.