

# HEUCOPHOS® ZAM-PLUS

in short oil alkyd



Solvent based

Heubach formulation No. 299-05

05/03

FUNCTION	PRODUCT	PRODUCER	PBW
Short oil alkyd	Vialkyd AF 342n/60X	Vianova Resins, today Cytec	34.55
Aromatic hydrocarbon	Xylene		18.55
Rheology modifier	Bentone SD-3	Rheox, today Elementis	0.40
Drier	Octa-Soligen Calcium 10	Borchers	0.10
<b>Premix.</b>			
Anticorrosive pigment	HEUCOPHOS® ZAM-PLUS	Heubach	10.00
Barium sulphate	Albaryt	Sachtleben	18.25
Magnesium silicate	Finntalc M10 E	Finnminerals, today Mondo Minerals	10.80
Titanium dioxide	Kemira 650	Kemira	6.00
<b>Grind.</b>			
Lead-free drier	Octa-Soligen Drier 173	Borchers	1.10
Antiskinning agent	Borchinox M 2	Borchers	0.25
<b>Add components separately while mixing.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
PVC in %			40.5
PVC / CPVC			0.7
Solids in %			67.0
Vol.-% Anticorrosive pigment reg. pigment/filler			22.0

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.