

Calcium Phosphate CP

In styrene-acrylic



Water based

Heubach formulation No. 06288

07/06

FUNCTION	PRODUCT	PRODUCER	PBW
Styrene-acrylic dispersion	Liocryl AS 603, 42%	Synthopol Chemie	30.00
Neutralizing agent	Ammonia, 25%		0.20
Glycol ether	Butyl glycol		5.00
Flash-rust inhibitor	Ser-AD FA 179	Elementis	0.50
Wetting and Dispersing agent	Disperse-Ayd W 22	Elementis	0.30
Defoamer	Byk-033	Byk-Chemie	0.30
Thickener	Rheolate 2001	Elementis	0.40
Preserving agent	Hydrol M	Biochema Schwaben	0.10
Premix.			
Iron oxide red	Bayferrox 130 M	Lanxess	7.40
Anticorrosive pigment	Calcium Phosphate CP	Heubach	5.95
Corrosion inhibitor	Alcophor 827	Cognis	1.80
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	6.35
Calcium carbonate	Millicarb	Omya	10.70
Antisettling agent	Aerosil R 972	Degussa, today Evonik	1.00
Grind 30 minutes with a bead mill.			
Styrene-acrylic dispersion	Liocryl AS 603, 42%	Synthopol Chemie	30.00
Add to the grind.			
			100.00

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.