

Heubach formulation No. 01214

11/01

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Epoxy	D.E.R. 671, 75% in Methoxypropanol	Dow	21.40
Wetting agent	Disperbyk-101	Byk-Chemie	0.50
Solvent	Aromatic 100	Exxon	1.50
Solvent	Methyl propyl ketone		3.80
Premix.			
Antisettling agent	Cab-O-Sil TS 720	Cabot	0.70
Iron oxide red	Bayferrox 222 FM	Bayer	5.60
Anticorrosive pigment	HEUCOPHOS® SRPP	Heubach	5.60
Silica alumina ceramic	Zeeosphere G-400	3M	15.20
Barium sulphate	Barytes BA-25	Engelhard	18.00
Magnesium silicate	Nicron 402	Luzenac America	4.50
Grind.			
Epoxy	D.E.R. 671, 75% in Methoxypropanol	Dow	5.40
Solvent	Isopropyl alcohol		1.10
Solvent	Methyl propyl ketone		4.40
Add while mixing.			
			87.70
Component B			
Curing agent	Ancamide 801 Curing Agent, 100%	Air Products	8.80
Solvent	Aromatic 100	Exxon	1.20
Solvent	Isopropyl alcohol		2.30
Mix.			
			12.30
Mix components A and B thoroughly prior to use.			

HEUCOPHOS[®] SRPP

in epoxy



Solvent based

Heubach formulation No. 01214

11/01

FUNCTION	PRODUCT	PRODUCER	PBW
			100.00
SPECIFICATIONS			
Solids in %			78.8

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.