

Full Shade Ca/Zn compound; 5% pigmentation
Product Description

Dry preparation of inorganic and/or organic pigments with unstabilized PVC.

| | |
|------------|---------------|
| Appearance | Violet powder |
|------------|---------------|

Technical Data

| | Unit | Value | Test Method |
|--------------------------|----------------------|----------|--------------------|
| Volatile matter (105 °C) | [%] | <1.0 | |
| Density | [g/cm ³] | typ. 1.4 | acc. to ISO 787-10 |
| Bulk density | [g/cm ³] | typ. 0.5 | acc. to ISO 697 |
| PVC K-value | | typ. 58 | |

PVC K-value is based on information from PVC supplier.

Fastness Properties
Resistance to Chemicals

| | Value | Test Method |
|--------|-------|-----------------------------------|
| Acid | 1 | rating acc. to DIN EN ISO 105-A03 |
| Alkali | 3 - 4 | rating acc. to DIN EN ISO 105-A03 |

Acid/alkali resistance: Product was dipped into hydrochloric acid (10%) or soda solution (10%). Rating with gray scale: 1=poor, 5=excellent.

| | Value | Test Method |
|-----------------------------|-------|-----------------------------------|
| Migration | 5 | rating acc. to DIN EN ISO 105-A03 |
| Heat resistance [°C] | 220 | |
| Light fastness [full shade] | 7 - 8 | rating acc. to DIN EN ISO 105-B02 |

Migration, heat resistance and light fastness are based on information from raw material supplier. The weather fastness of a colored rigid PVC is influenced by many factors especially the stabilization of the PVC-compound. Hence the weathering has to be tested in the polymer system of the user.

Packaging and Handling

| | |
|-----------|---|
| Packaging | 25 kg paper bags |
| Packaging | Different types of packaging are available on request |

Tds-hp_49001se-01_02

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.