

Heubach formulation No. 587-03

10/09

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Acrylic	Desmophen A 160, 60%	Bayer	21.85
Acrylic	Desmophen A 450, 50% in Butyl acetate/Xylene (1:1)	Bayer	7.30
Mix.			
Aromatic hydrocarbon	Xylene		3.95
Rheology modifier	Bentone 38	Elementis	0.45
Wetting and Dispersing agent	Anti-Terra-204	Byk-Chemie	0.15
Mix until uniform paste prior to addition.			
Defoamer	Modaflow, 1% in Xylene	Cytec	1.20
Defoamer	Byk-141	Byk-Chemie	0.25
Add while mixing.			
Solvent	Ethyl acetate		1.00
Solvent	Butyl acetate		1.00
Aromatic hydrocarbon	Xylene		1.00
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	4.80
Antisettling agent	Aerosil R 972	Evonik	0.15
Manganese ferrite	Bayferrox 303 T	Lanxess	0.20
Titanium dioxide	Tronox R-KB-5	Kerr-McGee	8.00
Magnesium silicate	Finntalc M15	Mondo Minerals	2.30
Barium sulphate	Blanc fixe micro	Sachtleben	25.85
Grind with a bead mill.			
Solvent	Ethyl acetate		1.00
Solvent	Butyl acetate		1.00
Aromatic hydrocarbon	Xylene		1.00

Heubach formulation No. 587-03

10/09

FUNCTION	PRODUCT	PRODUCER	PBW
Premix.			
Catalyst	Dibutylzinndilaurat		0.25
Add while mixing.			
			82.70
Component B			
Curing agent	Desmodur N 75, 75%	Bayer	6.35
Add.			
Solvent	Ethyl acetate		3.65
Solvent	Butyl acetate		3.65
Aromatic hydrocarbon	Xylene		3.65
Premix.			
			17.30
Mix components A and B thoroughly prior to use.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			15.0
PVC in %			34.7
PVC / CPVC			0.6
Solids in %			61.8

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.