

Heubach formulation No. 05261

05/05

FUNCTION	PRODUCT	PRODUCER	PBW
Epoxy	Epon Resin 828, 100%	Resolution, today Hexion	25.80
Antisettling agent	M-P-A 1078	Elementis	0.50
Anticorrosive pigment	HEUCOPHOS® SAPP	Heubach	5.90
Calcium metasilicate	10 AS Wollastocoat	Nyco Minerals	2.85
Magnesium aluminium silicate	Summit Chlorite	Speciality Minerals	8.30
Barium sulphate	Barytes BA-25	Engelhard	9.55
Antisettling agent	Cab-O-Sil TS 720	Cabot	0.60
<b>Grind.</b>			
Reactive diluent	Epodil L	Air Products	2.90
Solvent	Super Hi-Flash Naphtha	Ashland	9.80
Melamine resin	Beetle 216-8	Cytec	2.10
Aluminium paste	Aluminium paste L-243	Silberline	10.50
Solvent	Diacetone alcohol		2.00
Solvent	Super Hi-Flash Naphtha	Ashland	3.90
<b>Add while mixing.</b>			
			<b>84.70</b>
<b>Component B</b>			
Curing agent	Ancamide 2353 Curing Agent, 100%	Air Products	15.30
<b>Mix.</b>			
			<b>15.30</b>
<b>Mix components A and B thoroughly prior to use.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Solids in %			79.5

® = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.