

FUNCTION	PRODUCT	PRODUCER	PBW
Polyurethane dispersion	Bayhydrol VP LS 2917, 45%	Bayer	36.08
Drier	Octa-Soligen Cobalt 7 aqua	Borchers	0.12
Glycol ether	Butyl glycol		1.63
	Water		1.62
Wetting agent	Surfynol 104 BC	Air Products	0.49
Neutralizing agent	Triethylamine, 20%		1.90
<b>Premix.</b>			
Titanium dioxide	Bayertitan R-KB-2, today Tronox R-KB-2	Bayer, today Kerr-McGee	5.64
Iron oxide yellow	Bayferrox 3910	Bayer	1.13
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	8.80
Zinc oxide	Zinkweiss Harzsiegel Standard	Harzer Zinkoxyde Heubach, today Norzinco	1.54
Antisettling agent	Aerosil 300	Degussa, today Evonik	0.28
Magnesium silicate	Micro-Talc A.T. Extra	Mondo Minerals	8.77
Magnesium calcium carbonate	Microdol Super	Mondo Minerals	5.09
Aluminium silicate	Micro-Mica W1	Mondo Minerals	5.09
<b>Grind.</b>			
	Water		21.82
<b>Add while mixing.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Solids in %			50.0

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.