

Heubach formulation No. 00175

08/00

FUNCTION	PRODUCT	PRODUCER	PBW
Soluble alkyd	Kelsol 3950-B2G-70	Reichhold	25.40
Neutralizing agent	Ammonia, 25%		1.20
Solvent	Butyl alcohol		0.70
Glycol ether	Butyl glycol		2.30
Premix.			
Titanium dioxide	Kronos 2160	Kronos	8.50
Carbon black	Printex 140 V	Degussa, today Evonik	0.45
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	5.95
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.65
Magnesium silicate	Micro-Talc A.T. Extra	Mondo Minerals	7.50
Antisettling agent	Aerosil 200	Degussa, today Evonik	0.35
Grind.			
Drier	Additol VXW 4940	Cytec	0.45
Defoamer	Tego Foamex 1488	Tego Chemie	0.25
	Water		46.30
Add to the grind. Adjust pH 9.0 - 9.5 with ammonia.			
			100.00
SPECIFICATIONS			
PVC in %			31.4
Solids in %			41.4
Vol.-% Anticorrosive pigment reg. pigment/filler			25.7

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.