

Rohm and Haas formulation No. P-15-1

09/95

FUNCTION	PRODUCT	PRODUCER	PBW
Magnesium silicate	2610 Talc	Whittaker, Clark and Daniels	9.00
Calcium carbonate	Albaglos	Pfizer, today Speciality Minerals	9.00
Iron oxide red	Bayferrox 120 NM	Bayer	4.80
Anticorrosive pigment	HEUCOPHOS® ZMP	Heubach	4.80
Anticorrosive pigment	Shieldex	Grace	2.40
Rheology modifier	Bentone LT	Rheox, today Elementis	0.10
Defoamer	Foamaster AP	Henkel, today Cognis	0.20
	Water		11.70
Acrylic dispersion	Maincote PR-15, 47%	Rohm and Haas	44.10
Wetting agent	Tamol 165	Rohm and Haas	1.85
Wetting agent	Igepal CTA-639	GAF, today Rhodia	0.50
Grind with a sand mill, fineness of grind app. 10 microns.			
Glycol ether	Butyl Cellosolve	Union Carbide	7.30
Plasticizer	Dibutyl phthalate	Eastman	0.60
Solvent	Ethyl alcohol		2.10
Flash-rust inhibitor	Sodium nitrite, 15% in H ₂ O		1.05
Neutralizing agent	Ammonia, 14%		0.50
Add to the grind. Adjust pH 8.5 - 9.0 with ammonia.			100.00
SPECIFICATIONS			
PVC in %			35.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.