

Heubach formulation No 15422

11/15

FUNCTION	PRODUCT	PRODUCER	PBW
	Demi. water		12.04
Neutralizing agent	Ammonia, 28%		0.29
Wetting agent	Orotan 165	Dow	1.11
Defoamer	Drewplus L-493	Ashland	0.10
Glycol ether	Ethylene glycol monobutyl ether		3.85
Plasticizer	Dibutyl phthalate	Eastman	0.72
Titanium dioxide	Ti-Pure Rutile R-706	DuPont	8.80
Anticorrosive pigment	HEUCOPHOS® ZMP	Heubach	10.70
Magnesium silicate	Nyral 400	R.T. Vanderbilt	5.73
	Demi. water		2.31
Grind with a bead mill.			
	Demi. water		2.31
Rheology modifier	Bentone LT	Elementis	0.10
	Demi. water		1.16
Acrylic emulsion	Maincote PR-71, 50%	Dow	47.46
Neutralizing agent	Ammonia, 28%		0.20
Premix and add while mixing.			
Solvent	Ethyl alcohol		1.77
Flash-rust inhibitor	Sodium Nitrite, 15% in water		0.87
PU-thickener	Acrysol RM-8	Dow	0.38
Defoamer	Drewplus L-493	Ashland	0.10
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			38.8
PVC in %			24.7

HEUCOPHOS[®] ZMP

In acrylic emulsion



Water based

Heubach formulation No 15422

11/15

SPECIFICATIONS

PVC / CPVC

0.5

Solids in %

49.8

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.