

Heubach formulation No. 882-03

10/18

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Epoxy dispersion	BECKOPOX EP 387w/52WA	Allnex	46.95
	Demi. water		6.10
Wetting and dispersing agent	Additol VXW 6208/60	Allnex	2.05
Defoamer	Additol VXW 6393	Allnex	0.20
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZAM-PLUS	Heubach	5.00
Iron oxide yellow	Bayferrox 3920	Lanxess	0.40
Iron oxide black	Bayferrox 306	Lanxess	0.85
Titanium dioxide	Kronos 2190	Kronos	14.55
Barium sulphate	EWO	Deutsche Baryt-Industrie	12.50
Grind with a bead mill.			
Defoamer	Additol VXW 6393	Allnex	0.20
Ester alcohol	Texanol	Eastman	0.45
Thickener	Additol VXW 6388	Allnex	0.35
Levelling and wetting agent	Additol VXW 6503N	Allnex	0.20
			89.80
Component B			
Curing agent	BECKOPOX EH 613w/80WA	Allnex	5.10
	Demi. water		5.10
			10.20
			100.00
Mix components A and B thoroughly prior to use.			
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			17.7

HEUCOPHOS[®] ZAM-PLUS

In epoxy dispersion



Water based

Heubach formulation No. 882-03

10/18

SPECIFICATIONS

PVC in %	25.0
PVC / CPVC	0.4
Solids in %	63.6
Crosslinking in %	75.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.