

Heubach formulation No. 98141

08/98

FUNCTION	PRODUCT	PRODUCER	PBW
Long oil alkyd	Eterkyd 1106-M-70, 70%	Eternal Chemical	40.00
Rheology modifier	Bentone SD-3	Rheox, today Elementis	0.30
Solvent	White spirit		8.40
Drier	Octa-Soligen Calcium 10	Borchers	0.30
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	9.00
Barium sulphate	Albaryt	Sachtleben	24.00
Magnesium silicate	Finntalc M10	Finnminerals, today Mondo Minerals	10.00
Titanium dioxide	Kemira 650	Kemira	5.30
Grind.			
Lead-free drier	Octa-Soligen Drier 173	Borchers	2.40
Antiskinning agent	Borchinox M 2	Borchers	0.30
Add components separately while mixing.			
			100.00
SPECIFICATIONS			
Solids in %			78.0
Vol.-% Anticorrosive pigment reg. pigment/filler			18.7

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.