

Heubach formulation No. 02229

02/02

FUNCTION	PRODUCT	PRODUCER	PBW
	Water		6.00
Wetting agent	Tamol 165	Rohm and Haas	1.20
Levelling agent	Dow Corning 14 Additiv	Dow	0.30
Neutralizing agent	AMP-95	Angus Chemie	0.20
Defoamer	Foamaster 333	Cognis	0.10
Premix.			
Titanium dioxide	Ti-Pure Rutile R-900	DuPont	13.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	5.65
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.60
Grind.			
Acrylic-copolymer dispersion	Neocryl A-6085, 40%	Avecia, today DSM	60.20
Flash-rust inhibitor	Corrosion inhibitor L 1	Erbslöh	1.00
Glycol ether	Propylene glycol		3.60
Glycol ether	Arcosolv PM	Arco	3.60
Plasticizer	Dibutyl phthalate	Eastman	1.20
Defoamer	Dehydran 1293	Cognis	0.50
Levelling agent	Byk-301	Byk-Chemie	0.25
Wetting agent	Byk-346	Byk-Chemie	0.40
	Water		2.00
Thickener	Rheolate 300	Elementis	0.20
Add while mixing.			100.00
SPECIFICATIONS			
PVC in %			18.8
Vol.-% Anticorrosive pigment reg. pigment/filler			30.4

HEUCOPHOS[®] ZPO / HEUCORIN[®] RZ

in direct to metal one coat



Water based

Heubach formulation No. 02229

02/02

SPECIFICATIONS

Solids in %

47.1

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.