

Vianova Resins formulation No. KM 1372/2 / today Cytec

10/99

FUNCTION	PRODUCT	PRODUCER	PBW
Acrylic-copolymer dispersion	Viacryl VSC 6279 w/45 WA	Vianova Resins, today Cytec	58.70
Wetting agent	Surfynol CT 131	Air Products	0.50
Defoamer	Additol VXW 4909	Vianova Resins, today Cytec	0.40
Anticorrosive pigment	HEUCOPHOS® ZMP	Heubach	8.80
Calcium carbonate	Omyacarb 1T	Omya	6.60
Iron oxide red	Bayferrox 130 FS	Bayer	2.90
Magnesium silicate	Micro-Talc A.T. Extra	Mondo Minerals	4.10
Diatomaceous silica	Celite 281	Celite	3.00
Flash-rust inhibitor	Cotrol AMB, 15% in H ₂ O	CasChem	1.50
Plasticizer	TXIB Plasticizer	Eastman	1.50
Glycol ether	Methyl diglycol		2.50
Neutralizing agent	AMP-90	Angus Chemie	0.30
Antisettling agent	Winnofil SPT	ICI, today Solvay	0.70
Grind with a bead mill.			
PU-thickener	Rheolate 255, 4% in H ₂ O	Kronos Titan, today Elementis	0.50
	Water		8.00
Add while mixing.			
			100.00
SPECIFICATIONS			
Solids in %			53.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.