

Heubach formulation No 720-02

08/13

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Epoxy dispersion	BECKOPOX EP 2384w/57WA	Allnex	28.75
Wetting and dispersing agent	Additol VXW 6208/60	Allnex	1.05
Defoamer	Additol VXW 6393	Allnex	0.30
	Demi. water		5.90
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	3.55
Magnesium silicate	Micro-Talc I.T. Extra	Mondo Minerals	5.40
Titanium dioxide	Kronos 2190	Kronos	12.60
Iron oxide yellow	Bayferrox 3920	Lanxess	0.25
Iron oxide black	Bayferrox 306	Lanxess	0.60
Barium sulphate	EWO	Sachtleben	13.90
Grind.			
Ester alcohol	Texanol	Eastman	0.40
Defoamer	Additol VXW 6393	Allnex	0.20
Thickener	Additol VXW 6388	Allnex	0.20
Add while mixing.			
			73.10
Component B			
Curing agent	Laboratory product AHD 124-7/42WA	Allnex	26.90
			26.90
Mix components A and B thoroughly prior to use.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			9.9
PVC in %			28.5

HEUCOPHOS[®] ZPO

In epoxy dispersion



Water based

Heubach formulation No 720-02

08/13

SPECIFICATIONS

PVC / CPVC

0.5

Solids in %

64.3

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.