

Heubach formulation No. 816-08

09/16

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Component A</b>			
Epoxy dispersion	EPI-REZ 7520-WD-52	Hexion	36.60
Glycol ether	Dowanol PPH	Dow	2.80
Defoamer	FoamStar ED 2526	BASF	0.25
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	9.20
Titanium dioxide	Ti-Pure R-960	DuPont	7.60
Calcium metasilicate	Tremin 283-600 EST	HPF, Quarzwerke	7.50
Barium sulphate	Albawhite 80	Sachtleben	5.10
Muscovite	Mica SG	Aspanger	0.55
<b>Grind with a bead mill.</b>			
Epoxy dispersion	EPI-REZ 7520-WD-52	Hexion	9.75
Adhesion promoter	Silquest A-1871	Momentive	0.80
	Demi. water		7.65
<b>Add.</b>			<b>87.80</b>
<b>Component B</b>			
Curing agent	EPIKURE 6870-W-53	Hexion	12.10
Flash-rust inhibitor	Raybo 80	Raybo Products	0.10
			<b>12.20</b>
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			31.0
PVC in %			24.7
PVC / CPVC			0.5
Solids in %			60.4

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.