

	Value	Test Method
Heat resistance [°C]	600	acc. to ISO 787-21
Light fastness [full shade]	8	acc. to DIN EN ISO 16474-2/DIN EN ISO 105-B02
Light fastness [1/9 SD]	8	acc. to DIN EN ISO 16474-2/DIN EN ISO 105-B02
Weather fastness [full shade]	5	acc. to DIN EN ISO 16474-2/DIN EN ISO 20105-A02
Weather fastness [1/9 SD]	5	acc. to DIN EN ISO 16474-2/DIN EN ISO 20105-A02

Heat resistance: Tested in heat resistant coating up to 600 °C for 30 minutes.

Light Fastness: Tested in water based automotive system. Rating with 8-step wool scale: 1=poor, 8=excellent.

Weather fastness: Tested in water based automotive system. Rating with gray scale after 2000 h accelerated weathering: 1=poor, 5=excellent.

Packaging and Handling

Packaging	25 kg paper bags
Packaging	Different types of packaging are available on request

Tds-hdc_259c-01_02

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.