

HEUCOPHOS® ZPA / HEUCOPHOS® CAPP 75:25

In epoxy dispersion



Water based

Heubach formulation No. 967-15

03/20

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Epoxy dispersion	EPI-REZ Resin 7723-W-53	Hexion	33.65
Defoamer	FoamStar ED 2526	BASF	0.26
	Demi. water		9.05
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	6.40
Anticorrosive pigment	HEUCOPHOS® CAPP	Heubach	2.13
Titanium dioxide	Ti-Pure R-960	Chemours	8.42
Calcium metasilicate	Tremin 283-600 EST	HPF, Quarzwerke	8.27
Barium sulphate	Albawhite 80	SACHTLEBEN MINERALS	8.09
Muscovite	Mica SG	Aspanger	0.61
Grind with a bead mill.			
Epoxy dispersion	EPI-REZ Resin 7723-W-53	Hexion	8.74
Adhesion promoter	CoatOSil MP 200	Momentive	0.58
Flash-rust inhibitor	Raybo 80	Raybo Products	0.08
Add to the grind.			
			86.28
Component B			
Curing agent	EPIKURE Curing Agent 6870-W-53	Hexion	13.72
			13.72
Mix components A and B thoroughly prior to use.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			30.0
PVC in %			28.4

HEUCOPHOS[®] ZPA / HEUCOPHOS[®] CAPP 75:25

In epoxy dispersion



Water based

Heubach formulation No. 967-15

03/20

SPECIFICATIONS

PVC / CPVC	0.5
Solids in %	63.7
Crosslinking in %	70.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.