

Avecia formulation D-1836 / today DSM

09/02

FUNCTION	PRODUCT	PRODUCER	PBW
	Water		7.20
Neutralizing agent	AMP-95	Angus Chemie	0.10
Dispersing agent	Disperse-Ayd W 33	Elementis	1.20
Premix.			
Glycol ether	Butyl glycol		4.50
Titanium dioxide	Kronos 2190	Kronos	11.30
Magnesium silicate	Micro-Talc I.T. Extra	Mondo Minerals	8.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	10.70
Carbon black paste	Hostatint-Schwarz GR 30	Clariant	1.20
Grind with a bead mill, fineness of grind < 20 microns, temperature < 40 °C.			
Styrene-acrylic	NeoCryl PV-57-B	Avecia, today DSM	53.50
Ester alcohol	Texanol	Eastman	1.70
Flash-rust inhibitor	Ser-AD FA 179	Condea Servo	0.30
Defoamer	Drew 210-693	Ashland	0.30
			100.00
SPECIFICATIONS			
Solids in %			57.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.