

Bayer formulation No. SNM 55-90/6

02/89

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Component A</b>			
Polyester	Desmophen 680, 70% in Butyl acetate	Bayer	22.94
Defoamer	Modaflow, 1% in Xylene	Solutia, today Cytec	1.10
Defoamer	Byk-141, 4%	Byk-Chemie	0.22
<b>Premix.</b>			
Antisettling agent	Anti-Terra-U	Byk-Chemie	0.14
Solvent	Solvesso 100	Exxon	2.43
Rheology modifier	Bentone 38	Kronos Titan, today Elementis	0.29
<b>Mix until uniform paste prior to addition.</b>			
Aromatic hydrocarbon	Xylene		6.02
Solvent	Butyl acetate		6.02
Solvent	Butoxyl	Hoechst	4.01
<b>Mix.</b>			
Titanium dioxide	Bayertitan R-KB-2, today Tronox R-KB-2	Bayer, today Kerr-McGee	9.14
Iron oxide yellow	Bayferrox 415	Bayer	1.37
Aluminium silicate	ASP 600	Langer	22.85
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	9.55
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	5.86
Zinc oxide	Zinkweiss Harzsiegel F	Harzer Zinkoxyde Heubach, today Norzinco	0.11
<b>Grind.</b>			
			<b>92.05</b>
<b>Component B</b>			
Curing agent	Desmodur N 75, 75%	Bayer	7.95
<b>Add.</b>			
			<b>7.95</b>

Bayer formulation No. SNM 55-90/6

02/89

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Mix components A and B thoroughly prior to use.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
PVC in %			45.0
Solids in %			71.2
Vol.-% Anticorrosive pigment reg. pigment/filler			11.1

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.