

Heubach formulation No. 99152

08/99

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Component A</b>			
Epoxy	Araldite PY-306, 100%	Ciba, today Huntsman	25.60
Aromatic hydrocarbon	Xylene		2.40
Antisettling agent	M-P-A 1078 X	Elementis	0.15
<b>Premix.</b>			
Chromium oxide green	Chromoxidgrün GN-M	Bayer	1.60
Iron oxide yellow	Bayferrox 3920	Bayer	0.80
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	10.50
Calcium metasilicate	10 ES Wollastocoat	Nyco Minerals	15.70
<b>Grind.</b>			
			<b>56.75</b>
<b>Component B</b>			
Curing agent	Thermoset 65 Hardener, 100%	Thermoset Plastics	11.00
Aromatic hydrocarbon	Xylene		6.55
Antisettling agent	M-P-A 1078 X	Elementis	0.15
<b>Premix.</b>			
Titanium dioxide	Ti-Pure Rutile R-902	DuPont	5.90
Magnesium silicate	Beaverwhite 325	Cyprus Industrial Minerals	8.85
Antisettling agent	Imsil A-15	Illinois Minerals	3.90
<b>Grind.</b>			
Melamine resin	Beetle 216-8	Cytec	1.00
Aromatic hydrocarbon	Xylene		3.90
Solvent	Diacetone alcohol		2.00
<b>Add while mixing.</b>			
			<b>43.25</b>

Heubach formulation No. 99152

08/99

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Mix components A and B thoroughly prior to use.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Solids in %			84.3
Vol.-% Anticorrosive pigment reg. pigment/filler			19.1

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.