

Evonik Tego formulation No. P80X 9 002

10/20

FUNCTION	PRODUCT	PRODUCER	PBW
Methyl phenyl silicone resin	SILIKOPHEN P 80/X	Evonik	38.90
Wetting and Dispersing agent	Tego Dispers 670	Evonik	1.10
Wetting agent	Tego Wet 270	Evonik	0.10
Defoamer/Deaerator	Tego Airex 900	Evonik	0.50
Rheology modifier	BENTONE 38	Elementis	0.30
Solvent	Butyl glycol acetate		1.20
Solvent	Isobutyl alcohol		0.50
Aromatic hydrocarbon	Xylene		9.00
Copper chromite black spinel	HEUCODUR®-Black 9-100	Heubach	5.90
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	5.90
Muscovite mica	Mica TM	Aspanger	14.80
Antisettling agent	Aerosil 200	Evonik	0.50
Grind with a bead mill.			
Methyl phenyl silicone resin	SILIKOPHEN P 80/X	Evonik	10.50
Aromatic hydrocarbon	Xylene		10.80
Add while stirring.			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			20.0
PVC in %			20.0
Solids in %			68.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.