

Eastman formulation No. A-2431-78

02/03

FUNCTION	PRODUCT	PRODUCER	PBW
	Water		12.88
Dispersing agent	Orotan 681	Rohm and Haas	3.48
Levelling agent	Troysol LAC	Troy Chemical	0.99
Neutralizing agent	AMP-90	Angus Chemie	0.20
Defoamer	Byk-020	Byk-Chemie	0.10
Iron oxide yellow	Bayferrox 3920	Bayer	4.97
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	4.97
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.99
Magnesium silicate	Nytal 400	R.T. Vanderbilt	12.43
Grind to a fineness of app. 30 microns.			
	Water		7.03
Styrene-acrylic	Sokrat 2431	Eastman	46.72
Neutralizing agent	Ammonia		0.25
Premix and add while mixing.			
Glycol ether	Eastman EB	Eastman	2.50
Corrosion inhibitor	Emadox D520	Labema	1.00
Premix and add while mixing.			
PU-thickener	Acrysol RM-8 W	Rohm and Haas	0.99
PU-thickener	Acrysol RM-2020	Rohm and Haas	0.50
Add while mixing.			
			100.00
SPECIFICATIONS			
PVC in %			24.6

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.