

FUNCTION	PRODUCT	PRODUCER	PBW
	Water		19.60
Wetting agent	Orotan 731	Rohm and Haas	2.50
Wetting agent	Triton CF-10	Union Carbide	0.40
PU-thickener	Acrysol RM-8, 14% in H ₂ O	Rohm and Haas	1.50
Defoamer	Agitan 295	Münzing	0.10
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	6.10
Magnesium silicate	Micro-Talc A.T. Extra	Mondo Minerals	7.10
Aluminium silicate	Micro-Mica W1	Mondo Minerals	4.70
Iron oxide black	Bayferrox 318 M	Bayer	4.70
Grind with a bead mill.			
Alkyd emulsion	Uradil Az554 Z-50	DSM Coating Resins	50.90
Defoamer	Agitan 295	Münzing	0.10
Drier	Servosyn WEB Cobalt 8%, today Nuodex WEB Cobalt 8%	Servo, today Condea Servo	0.50
Flash-rust inhibitor	Ser-AD FA 179	Servo, today Condea Servo	0.30
PU-thickener	Ser-AD FX 1010, 50% in H ₂ O	Servo, today Condea Servo	1.50
Add while mixing.			100.00
SPECIFICATIONS			
PVC in %			22.2
PVC / CPVC			0.5
Solids in %			50.7
Vol.-% Anticorrosive pigment reg. pigment/filler			25.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.