

Air Products formulation

09/98

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Epoxy	D.E.R. 671, 75% in Methoxypropanol	Dow	15.15
Epoxy	D.E.R. 331, 100%	Dow	5.05
Dispersing agent	Nuosperse 657	Nuodex	0.40
Premix.			
Rheology modifier	Bentone SD-2	Elementis	0.20
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	9.70
Barium sulphate	Sparmite F	Elementis, today Speciality Minerals	16.90
Pigment	Chromium oxide green	Elementis	7.20
Calcium metasilicate	10 ES Wollastocoat	Nyco Minerals	14.20
	Nevoxy EPXL5	Neville	1.90
Grind.			
Melamine resin	Beetle 216-10	Cytec	2.50
Solvent	Aromatic 100	Exxon	2.10
Solvent	Isopropyl alcohol		2.40
Solvent	Methyl propyl ketone		9.70
Add while mixing.			
			87.40
Component B			
Curing agent	Ancamide 802 Curing Agent, 100%	Air Products	8.95
Solvent	Aromatic 100	Exxon	1.90
Solvent	Methyl propyl ketone		1.75
Mix.			
			12.60
Mix components A and B thoroughly prior to use.			

Air Products formulation

09/98

FUNCTION	PRODUCT	PRODUCER	PBW
			100.00
SPECIFICATIONS			
PVC in %			34.3
Solids in %			77.3

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.