

### Product Description

Chemical characterization	Zinc molybdenum orthophosphate hydrate
---------------------------	----------------------------------------

Excellent results have been achieved by applying HEUCOPHOS® ZMP in water based coating systems using one-part polyurethanes and acrylics.

### Technical Data

	Unit	Value	Test Method
Zinc as Zn	[% ]	53.5 - 56.5	acc. to ISO 6745
Molybdenum as MoO <sub>3</sub>	[% ]	1.2 - 2.2	ICP-OES
Phosphorous as PO <sub>4</sub> <sup>3-</sup>	[% ]	37.0 - 40.0	acc. to ISO 6745
Water-soluble chloride	[% ]	max. 0.025	acc. to ISO 787-13
Water-soluble sulphate	[% ]	max. 0.05	acc. to ISO 787-13
Lead as Pb	[ppm]	max. 10	ICP-OES
Cadmium as Cd	[ppm]	max. 10	ICP-OES
Loss on ignition 600 °C	[% ]	6.0 - 9.0	acc. to ISO 6745
Conductivity	[µS/cm]	max. 250	acc. to ISO 787-14
pH value		5.5 - 7.5	acc. to ISO 787-9
Density	[g/cm <sup>3</sup> ]	typ. 3.5	acc. to ISO 787-10
Bulk density	[g/cm <sup>3</sup> ]	typ. 0.4	
Tamped density	[g/cm <sup>3</sup> ]	typ. 0.9	acc. to ISO 787-11
Oil absorption	[g/100g]	typ. 25	acc. to ISO 787-5
Sieve residue 32 µm	[% ]	max 0.01	acc. to ISO 787-7
Average particle size	[µm]	2.0 - 3.5	acc. to ISO 13319

Tds-ac\_zmp-01\_02

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.

Application Profile			
Solvent based coatings			
Short and medium oil alkyds	++		●
Long oil alkyds			
High solids alkyds	+	✓	●
2K Epoxies	+		
Epoxy esters	+		
High solids epoxies	+	✓	
2K Polyurethanes			
High solids polyurethanes		✓	
Moisture cured polyurethanes			
Silicone resins			
Water based coatings			
Alkyd emulsions	+	✓	●
2K Epoxies	++	✓	
1K Polyurethanes	+++	✓	●
2K Polyurethanes	+	✓	
Silicone resins		✓	
Acrylic and modified acrylics	+++	✓	●
Butadiens	++	✓	
Specialty coatings			
Coil coatings			
Aircraft primers			
Wash and shop primers			
Direct to metal	+		
UV cured systems	+++	✓	
Powder coatings		✓	

+++ Excellent choice

++ Good choice

+ Possible choice

✓ Resin with low or no VOCs

● Additionally recommended in combination with HEUCORIN® RZ

**Tds-ac\_zmp-01\_02**

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.