

# HEUCOPHOS® ZCP-PLUS

In styrene-acrylic emulsion



Water based

Heubach formulation No. 755-09

07/14

FUNCTION	PRODUCT	PRODUCER	PBW
	Demi. water		9.10
Dispersing agent	Nuosperse W-30	Elementis	1.60
Glycol ether	Butyl glycol		6.00
Flash-rust inhibitor	Nalzin FA 379	Elementis	0.65
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	8.45
Titanium dioxide	Kronos 2190	Kronos	8.75
Magnesium silicate	Micro-Talc I.T. Extra	Mondo Minerals	5.80
Styrene-acrylic emulsion	NeoCryl XK-87, 51%	DSM NeoResins	19.50
Carbon black paste	Hostatint-Schwarz GR 30	Clariant	1.35
<b>Grind.</b>			
<b>Letdown:</b>			
Styrene-acrylic emulsion	NeoCryl XK-87, 51%	DSM NeoResins	35.35
Ester alcohol	Texanol	Eastman	2.30
Corrosion inhibitor	Nacorr 1652	King Industries	0.65
Defoamer	Drewplus TS-4380	Ashland	0.40
Thickener	Viscoatex 46	Coatex	0.10
			<b>100.00</b>
<b>Adjust pH 8.0 - 8.3 with ammonia, 25%.</b>			
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			36.5
PVC in %			21.7
PVC / CPVC			0.5
Solids in %			51.0

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.