

DSM Coating Resins formulation No. AZ06020

02/06

FUNCTION	PRODUCT	PRODUCER	PBW
	Water		8.75
Dispersing agent	Disperse-Ayd W 28	Elementis	2.00
Defoamer	Agitan 295	Münzing	0.10
Rheology modifier	Nuvis FX 1025	Elementis	0.30
Titanium dioxide	Kronos 2190	Kronos	13.00
Barium sulphate	Blanc fixe micro	Sachtleben	7.00
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	5.00
Anticorrosive pigment	HEUCOPHOS® ZAPP	Heubach	8.00
Grind at high speed			
	Water		6.40
Add while mixing.			
Alkyd emulsion	Uradil Az554 Z-50	DSM Coating Resins	44.00
Drier	Durham VX 71	Elementis	1.10
Flash-rust inhibitor	Ser-AD FA 179	Elementis	0.25
Rheology modifier	Nuvis FX 1070	Elementis	1.45
	Water		2.65
Add while mixing.			
			100.00
SPECIFICATIONS			
PVC in %			31.6
Solids in %			55.4

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.