

# Calcium Phosphate CP

In water soluble alkyd



Water based

Heubach formulation No. 06276

06/06

FUNCTION	PRODUCT	PRODUCER	PBW
Water soluble alkyd	WorléeSol 61 A, 75% in Butyl glycol/ sec. Butanol 1:1	Worlée	11.70
Neutralizing agent	Ammonia, 25%		0.50
<b>Water soluble after neutralisation with Ammonia, 25%.</b>			
	Demi. water		20.00
Glycol ether	Dowanol PnB	Dow	1.20
<b>Add.</b>			
Magnesium silicate	Mistron 75-6A	IMCD	4.05
Calcium carbonate	Omyacarb 2-AL	Omya	8.25
Anticorrosive pigment	Calcium Phosphate CP	Heubach	6.00
Corrosion inhibitor	Loxanol MI 6627	BASF	1.80
Iron oxide red	BAYFERROX 130 M	LANXESS	7.20
Drier	Nuodex WEB Cobalt 8%	Venator	0.25
Drier	Nuodex WEB Manganese 9%	Venator	0.20
Wetting agent	Hydropalat 535 N	BASF	0.50
<b>Grind 20 minutes with a bead mill.</b>			
	Demi. water		2.90
Glycol ether	Butyl glycol		1.70
<b>Add while stirring.</b>			
Water soluble alkyd	WorléeSol 61 A, 75% in Butyl glycol/ sec. Butanol 1:1	Worlée	12.70
Neutralizing agent	Ammonia, 25%		0.60
<b>Water soluble after neutralisation with Ammonia, 25%.</b>			
	Demi. water		18.75
<b>Premix and add to the grind.</b>			
Antiskinning agent	Exkin 2	Venator	0.10

# Calcium Phosphate CP

In water soluble alkyd



Water based

Heubach formulation No. 06276

06/06

FUNCTION	PRODUCT	PRODUCER	PBW
Glycol ether	Dowanol PnB	Dow	1.60
<b>Add to the grind. Adjust pH 8,2 - 8,5 with ammonia.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			24.8
PVC in %			34.3

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.