

Wacker formulation No. 604159

05/03

FUNCTION	PRODUCT	PRODUCER	PBW
Silicone powder	Silres 604	Wacker	46.50
Curing agent	Vestagon B 1530	Degussa, today Evonik	1.15
Pigment black	Ferro PK 3095	Ferro	6.25
Mica	Glimmer SC	Microfine Minerals	14.30
Anticorrosive pigment	HEUCOPHOS® SAPP	Heubach	13.40
Magnesium silicate	Talkum EL-10	Naintsch, today Luzenac	17.70
Degassing agent	Benzoin	Fluka	0.25
Levelling agent	Resiflow PV 88	Worlée	0.45
			<b>100.00</b>

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.