

Heubach formulation No. 974-06

06/20

FUNCTION	PRODUCT	PRODUCER	PBW
Vinyl modified epoxy ester	WATERSOL HY 3350, 43% W/BG	DIC Performance Resins	70.64
Wetting and Dispersing agent	Metolat 394	Münzing	0.82
Premix.			
Anticorrosive pigment	HEUCOPHOS® CAPP	Heubach	5.86
Calcium carbonate	Omycarb 2-AL	Omya	3.95
Magnesium silicate	Luzenac 20MO	Imerys	5.35
Titanium dioxide	KRONOS 2310	KRONOS	5.35
Antisettling agent	AEROSIL R 972	Evonik	0.86
Iron oxide red	BAYFERROX 130 M	LANXESS	0.35
Grind with a bead mill.			
Defoamer	FoamStar SI 2216	BASF	0.52
	Demi. water		4.64
Premix and add while stirring.			
Wetting agent	Hydropalat WE 3221	BASF	0.52
Neutralizing agent	Triethylamine		0.10
	Demi. water		0.52
Drier	ADDITOL VXW 4940 N	Allnex	0.52
Add to the grind.			
			100.00
Adjust pH 9,9 - 10 with Triethylamine.			
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			30.0
PVC in %			21.7
PVC / CPVC			0.4
Solids in %			52.1

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.