

Bayer formulation No. SJG 25044

05/97

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Acrylic dispersion	Bayhydrol VP LS 2235, 45%	Bayer	32.75
Wetting agent	Surfynol 104 E	Air Products	0.33
Defoamer	Bevaloid 770	Rhone-Poulenc, today Erbslöh	0.44
Iron oxide red	Bayferrox 130 BM	Bayer	4.48
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	16.36
Anticorrosive pigment	HEUCOPHOS® SAPP	Heubach	14.41
Silicon dioxide	Sikron-Feinstmehl F500	Quarzwerte	13.54
	Water		7.10
Grind 20 minutes at 12 m/s.			
Flash-rust inhibitor	Corrosion inhibitor L 1	Erbslöh	0.55
PU-thickener	Acrysol RM-8, 20% in Isopropyl alcohol	Rohm and Haas	0.11
Add while mixing.			
			90.07
Component B			
Curing agent	Desmodur N 3600	Bayer	7.94
Solvent	Methoxypropyl acetate		1.99
Mix.			
			9.93
Mix components A and B thoroughly prior to use.			
			100.00
Add water to obtain processing viscosity.			
SPECIFICATIONS			
PVC in %			44.0
Solids in %			71.5

® = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.