

FUNCTION	PRODUCT	PRODUCER	PBW
Silicone resin	SILIKOPHEN P 80/X	Evonik Tego Chemie	42.50
Dispersing agent	Tego Dispers 670	Evonik Tego Chemie	1.00
Rheology modifier	Bentone 38	Elementis	0.30
Solvent	Isobutyl alcohol		0.50
Solvent	Butyl glycol acetate		1.20
Deaerator	Tego Airex 900	Evonik Tego Chemie	0.50
Spinel black	HEUCODUR®-Schwarz 9-100	Heubach	6.30
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	4.90
Mica	Mica TM	Aspanger	17.80
Antisettling agent	Aerosil 200	Evonik	0.50
Aromatic hydrocarbon	Xylene		24.50
			<b>100.00</b>