

DSM Coating Resins formulation No. AZ06030

02/06

| FUNCTION | PRODUCT | PRODUCER | PBW |
|-----------------------------|---------------------|--------------------|---------------|
| | Water | | 16.80 |
| Dispersing agent | Disperse-Ayd W 28 | Elementis | 1.70 |
| Defoamer | Agitan 295 | Münzing | 0.05 |
| PU-thickener | Acrysol RM-825 | Rohm and Haas | 0.35 |
| Iron oxide red | Bayferrox 130 M | Bayer | 13.45 |
| Magnesium calcium carbonate | Microdol A 1 | Mondo Minerals | 6.70 |
| Magnesium silicate | Micro-Talc A.T.1 | Mondo Minerals | 4.75 |
| Anticorrosive pigment | HEUCOPHOS® ZAPP | Heubach | 8.15 |
| Grind at high speed | | | |
| Alkyd emulsion | Uradil XP 7600 AZ | DSM Coating Resins | 43.85 |
| PU-thickener | Acrysol RM-1020 | Rohm and Haas | 3.35 |
| Drier | Nuodex WEB combi AQ | Elementis | 0.50 |
| Flash-rust inhibitor | Ser-AD FA 179 | Elementis | 0.35 |
| Add while mixing. | | | 100.00 |
| SPECIFICATIONS | | | |
| PVC in % | | | 30.0 |
| Solids in % | | | 57.2 |

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.