

Heubach formulation No. 964-03

03/20

FUNCTION	PRODUCT	PRODUCER	PBW
	Demi. water		9.80
Wetting and dispersing agent	EDAPLAN 490	MÜNZING	1.20
Neutralizing agent	AMP-90	ANGUS Chemie	0.05
Defoamer	BYK-024	BYK-Chemie	0.10
Anti-corrosive pigment	HEUCOPHOS® CMP	Heubach	2.10
Titanium dioxide	KRONOS 2190	KRONOS	12.10
Grind with a bead mill.			
Acrylic dispersion	ALBERDINGK AC 2403, 47%	Alberdingk Boley	71.00
Defoamer	BYK-024	BYK-Chemie	0.10
Surfactant	BYK-349	BYK-Chemie	0.30
Coalescing agent	Eastman Optifilm Enhancer 300	Eastman Chemical	2.00
Flash-rust inhibitor	HEUCOFLASH™ LQ2	Heubach	0.45
Rheology modifier	TAFIGEL PUR 60, 10% in BG/demi. water 10:80	MÜNZING	0.80
Add while stirring.			
			100.00
Adjust pH 8,5-9,5 with AMP 90.			
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			20.0
PVC in %			10.8
PVC / CPVC			0.2
Solids in %			47.6

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.