

Solutia formulation No. Hg166 / today Cytec

04/01

FUNCTION	PRODUCT	PRODUCER	PBW
Acrylic dispersion	Viacryl VSC 6265 w/40 WA	Solutia, today Cytec	46.80
Neutralizing agent	AMP-90	Angus Chemie	0.20
Ester alcohol	Texanol	Eastman	0.50
Glycol ether	Methyl diglycol		1.50
Iron oxide yellow	Bayferrox 915 FS	Bayer	3.00
Titanium dioxide	Kronos 2059	Kronos	13.20
Calcium carbonate	Hydrocarb L	Omya	7.50
Barium sulphate	EWO	Alberti	8.50
Anticorrosive pigment	HEUCOPHOS® ZMP	Heubach	5.00
Diatomaceous silica	Celite 281	Celite	3.00
Rheology modifier	Thixatrol GST	Kronos, today Elementis	0.70
Wetting agent	Additol XL 270	Solutia, today Cytec	0.40
Defoamer	Additol VXW 4909	Solutia, today Cytec	0.50
Defoamer	Additol XW 372	Solutia, today Cytec	0.30
Grind with a bead mill.			
PU-thickener	Acrysol RM-2020	Rohm and Haas	0.70
	Water		7.00
Defoamer	Additol XW 372	Solutia, today Cytec	0.20
Flash-rust inhibitor	Cotrol AMB, 15% in H ₂ O	CasChem	1.00
Add while mixing.			100.00
SPECIFICATIONS			
Solids in %			60.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.