

## Clariant formulation No. 11/B30HH, today Kuraray Specialities

02/01

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Component A</b>			
Polyvinyl butyral	Mowital B 30 HH, 100%	Clariant, today Kuraray Specialities	3.40
Solvent	Butyl alcohol		5.10
Aromatic hydrocarbon	Xylene		8.50
<b>Mix until uniform solution prior to addition.</b>			
Polytetrafluoroethylene	Hostaflon TF 9205, today Dyneon TF 9205	Hoechst, today Dyneon	1.50
<b>Add while mixing.</b>			
Epoxy	Beckopox EP 301/75X	Vianova Resins, today Cytec	7.40
Glycol ether	Solvenon PM	BASF	3.60
<b>Mix until uniform solution prior to addition.</b>			
Epoxy	Beckopox EP 151, 100%	Vianova Resins, today Cytec	8.00
<b>Mix.</b>			
Magnesium silicate	Micro-Talc I.T. Extra	Mondo Minerals	6.00
Iron oxide black	Bayferrox 306	Bayer	3.00
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	8.00
Carbon black	Farbruß FW 2	Degussa, today Evonik	0.30
Calcium carbonate	Millicarb	Omya	22.70
<b>Grind.</b>			
Aromatic hydrocarbon	Xylene		3.40
Antisettling agent	Wacker HDK H 15	Wacker	0.40
Wetting agent	Additol XL 270	Vianova Resins, today Cytec	0.20
<b>Mix until uniform paste prior to addition.</b>			
Polyester	Haftharz LTW/ 60 X	Degussa, today Evonik	1.50
Aromatic hydrocarbon	Xylene		8.00
Solvent	Butyl alcohol		2.00

Clariant formulation No. 11/B30HH, today Kuraray Specialities

02/01

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Add while mixing.</b>			
			<b>93.00</b>
<b>Component B</b>			
Curing agent	Beckopox EH 651/70 X	Vianova Resins, today Cytec	7.00
<b>Add.</b>			
			<b>7.00</b>
<b>Mix components A and B thoroughly prior to use.</b>			
			<b>100.00</b>

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.