

Worlée formulation No. 1.3990-05

09/08

FUNCTION	PRODUCT	PRODUCER	PBW
High solids alkyd	WorleeKyd TT 3502	Worlée	29.80
Dispersing agent	Soja-Lecitin-Concentrate STA	Lubrizol	0.30
Rheology modifier	Bentone SD-2	Elementis	0.20
Antisettling agent	Aerosil 200	Degussa, today Evonik	0.30
Titanium dioxide	Kronos 2190	Kronos	6.10
Manganese ferrite	Bayferrox 303 T	Bayer, today Lanxess	0.40
Magnesium silicate	Finntalc M15	Mondo Minerals	8.20
Magnesium aluminium silicate	Plastorit M	Luzenac	8.20
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	6.10
Magnesium calcium carbonate	Microdol 1	Mondo Minerals	18.50
Grind.			
Glycol ether	Solvenon PM	BASF	2.00
Solvent	Methoxypropyl acetate		4.10
Aromatic hydrocarbon	Xylene		14.90
Drier	Octa-Soligen Calcium 10	Borchers	0.40
Drier	Cozirk 69	OMG	0.20
Antiskinning agent	Exkin 2	Elementis	0.30
Add components separately while mixing.			100.00
SPECIFICATIONS			
Solids in %			71.4

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.