

Evonik Tego formulation No. TOP E 900 9 003

10/20

FUNCTION	PRODUCT	PRODUCER	PBW
Silicone polyester hybrid resin	SILIKOTOP E 900	Evonik	20.40
Wetting and Dispersing agent	TEGO Dispers 652	Evonik	1.20
Rheology modifier	BENTONE SD-2	Elementis	0.20
Molecular sieve powder	SYLOSIV A 3	Grace	0.30
Antisettling agent	AEROSIL R 972	Evonik	0.90
Magnesium silicate	Micro-Talc I.T. Extra	Elementis	6.00
Kaolin	Polperse 50	Imerys	5.80
Carbon black pigment	Colour Black FW 200	Orion Engineered Carbons	0.10
Quartz	SIKRON SF6000	HPF, Quarzwerke	3.00
Barium sulphate	EWO	SACHTLEBEN MINERALS	11.10
Titanium dioxide	KRONOS 2190	KRONOS	10.50
Anticorrosive pigment	HEUCOPHOS® CAPP	Heubach	4.20
Solvent	Shellsol D 60	Shell	3.50
Solvent	Methoxypropyl acetate		2.20
Solvent	Butyl acetate		4.90
<b>Grind with a bead mill.</b>			
Silicone polyester hybrid resin	SILIKOTOP E 900	Evonik	16.30
Catalyst	TIB KAT 218, 1% in Butyl acetate	TIB Chemicals	3.00
Solvent	Butyl acetate		4.00
Solvent	Butyl acetate		2.40
<b>Add while stirring.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			12.8
PVC in %			30.4

# HEUCOPHOS<sup>®</sup> CAPP

In silicone resin



*Solvent based*

Evonik Tego formulation No. TOP E 900 9 003

10/20

## SPECIFICATIONS

Solids in %

76.0

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.