

Heubach formulation No. 370-07

12/08

FUNCTION	PRODUCT	PRODUCER	PBW
Soluble alkyd	Synthatat W 30, 75%	Synthopol Chemie	25.80
Neutralizing agent	Ammonia, 12%		2.30
Drier	Additol VXW 4940	Cytec	1.50
Premix.			
Wetting agent	Disperbyk-182	Byk-Chemie	0.60
Glycol ether	Butyl glycol		2.80
	Water		24.90
Antiskinning agent	Borchinox M 2	Borchers	0.40
Defoamer	Byk-020	Byk-Chemie	0.60
Titanium dioxide	Kronos 2190	Kronos	4.80
Iron oxide yellow	Bayferrox 3920	Lanxess	1.90
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	7.60
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.80
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	12.70
Antisettling agent	Aerosil R 972	Degussa, today Evonik	0.80
	Water		12.50
Grind.			
			100.00
Adjust pH 8,5 with ammonia, 25%			
SPECIFICATIONS			
PVC in %			34.2
PVC / CPVC			0.6
Solids in %			48.0
Vol.-% Anticorrosive pigment reg. pigment/filler			24.3

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.